



When it rains, it drains!

With Sport Drain_{MAX}, less is more!

A large, artificial putting green with multiple holes and flags, set in a landscaped area with trees and a building in the background.



Benefits:

- Patent Pending

SPERFEGGIMENTI

PRODUCT SHEET

SPORT DRAIN_{MAX}

The drainage material is comprised of recycled cross-linked polyethylene foam bonded with non-woven geotextile on one side of the mat. The product is grooved to promote the product's exceptional drainage capability. The drainage material conforms to the values and test methods listed below:

PROPERTY	MEASURE	TEST	VALUE
MATERIAL CHARACTERISTICS			
Dimensions ¹			48" x 210' (+/- 5 mm)
Composition	95% Recycled, non-contaminated, post industrial, cross-link, closed cell polyethylene foam		
Weight	Direct		0.9 LBS SF
Thickness	Direct	ASTM 5199	20 mm (+/- 2 mm)
Density	Average	ASTM 3575 Suffix W	10 — 12 LBS/FT ³
Tensile Strength		ASTM D 4595	MD: 40 lbs/inch / TD 39 lbs/inch
HYDRAULIC BEHAVIOR			
Transmissivity ²		ASTM 4716, GRI GC-8	
	Average	500 PSF: 1% Slope	4x10E-02 m2/sec
	Average	500 PSF: 1% Slope	>200 Gal/min/ft
Permittivity	Average	ASTM D 4491	3.235 sec-1
Permeability	Minimum	ASTM D 2434	>34 gal/min/SF
Infiltration Rate	Minimum	BS 7044 Method 4	42 in/hr
FIELD PERFORMANCE			
Shock Attenuation ³	Average	ASTM F 355-A	97 G _{MAX} (Concrete) : HIC 252
			88 G _{MAX} (Aggregate) : HIC 204

- Standard Roll Size 48" x 210', Also available in sheets. Custom rolls sizes available.
- Transmissivity tested by manufacturer every 100,000 square feet of product per ASTM D4716. Testing conditions are: steel plate / geocomposite / geomembrane / steel plate. The seating period is 100 hours.
- Infield GMAX tests available upon request using a variety of infill materials.

FEBRUARY 2009



WWW.3RFOAM.COM

3R FOAM

Exclusively Distributed by:

Recycled Foam Technologies, LLC

4223 Rock Run Road, Havre de Grace, MD 21078

Phone: 410-878-6341 Fax: 410-734-4129

Sport Drain_{MAX} is manufactured for Recycled Foam Technologies, LLC. The information contained herein has been accurately compiled by 3R FOAM, LLC, and to the best of our knowledge accurately represents 3R FOAM product. Final determination of the suitability of any information or material for the use contemplated and its manner is the sole responsibility of the users.